

2017 Boulevard Significant Drill Results

Drill hole	From (m)	To (m)	Length (m)	Au (g/t) by Fire Assay	Au (g/t) by Screen Metallics (Coarse Fraction >106 microns)	Au (g/t) by Screen Metallics (Fine Fraction <106 microns)	Au (g/t) by Screen Metallics (Weighted Average)
BV17-58	53.50	55.00	1.50	1.63	76.2	1.01	3.1
And	91.50	95.00	3.50	0.40	-	-	-
BV17-60	13.00	17.50	4.50	3.10	14.0	2.56	3.0
BV17-61	81.00	88.00	7.00	0.47	-	-	-
BV17-62	41.00	42.00	1.00	0.61	-	-	-
And	92.00	99.00	7.00	0.10	-	-	-
BV17-59	52.00	60.00	8.00	0.49	-	-	-
Incl.	52.00	55.90	3.90	0.80	-	-	-
Incl.	52.00	53.27	1.27	1.00	0.8	0.89	0.9
BV17-63	9.00	10.50	1.50	1.03	0.9	0.94	0.9
And	34.00	34.68	0.68	4.43	1.7	3.81	3.8
And	54.50	56.00	1.50	0.61	-	-	-
And	79.65	87.50	7.85	0.45	-	-	-
Incl.	79.65	84.25	4.60	0.62	-	-	-
Incl.	81.25	83.25	2.00	0.99	1.2	0.95	1.0
BV17-64	35.70	39.00	3.30	1.38	-	-	-
Incl.	35.70	36.85	1.15	3.30	3.3	3.35	3.4
And	65.35	65.50	0.15	1.59	19.2	0.68	1.2
BV17-65	14.50	20.30	4.30	2.58	-	-	-
Incl.	16.00	17.40	1.40	5.02	42.7	2.01	3.2
Incl.	17.90	19.20	1.30	2.35	8.1	2.66	2.3
And	77.20	77.50	0.30	0.45	-	-	-
And	129.00	129.50	0.50	2.27	4.7	1.62	1.7
BV17-66	56.00	57.00	1.00	0.76	-	-	-
And	77.15	77.50	0.35	2.69	1.8	2.76	2.7
And	86.35	86.65	0.30	0.55	-	-	-
BV17-67	19.25	20.85	1.60	1.39	1.0	1.26	1.2

Length represents the apparent thickness of the mineralization and should not be considered as the true width